

Grilamid® L 20 W 20 grey 9280

Polyamide 12

EMS-GRIVORY

Message:

Grilamid® L 20 W 20 grey 9280 is a Polyamide 12 (Nylon 12) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for extrusion.

Important attributes of Grilamid® L 20 W 20 grey 9280 are:

- Flame Rated
- RoHS Compliant
- Plasticized
- Good Flexibility
- Medium Viscosity
- Typical applications include:
 - Automotive
 - Consumer Goods
 - Electrical/Electronic Applications
 - Engineering/Industrial Parts
 - Hose/Tubing

General Information				
Additive		Plasticizer		
Features	Good Flexibility			
	Good Wear Resistance			
	Low Friction			
	Medium Viscosity			
	Plasticized			
Uses	Automotive Applications			
	Consumer Applications			
	Electrical/Electronic Applications			
	Engineering Parts			
	Industrial Applications			
	Tubing			
	Wire & Cable Applications			
RoHS Compliance		RoHS Compliant		
Appearance		Grey		
Forms		Granules		
Processing Method		Extrusion		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.03	--	g/cm³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.0	--	%	
Flow	0.80	--	%	

Water Absorption				ISO 62
Saturation, 23°C	1.5	--	%	
Equilibrium, 23°C, 50% RH	0.70	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Shore Hardness (Shore D, 15 sec)	--	64		ISO 868
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	650	500	MPa	ISO 527-2
Tensile Stress				ISO 527-2
Yield	30.0	30.0	MPa	
Break	60.0	60.0	MPa	
Tensile Strain (Yield)	20	20	%	ISO 527-2
Nominal Tensile Strain at Break	> 50	> 50	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	--	3.0	kJ/m ²	
23°C	9.0	40	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	100	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	45.0	--	°C	ISO 75-2/A
Continuous Use Temperature				Internal Method
-- ¹	80.0 to 110	--	°C	
-- ²	150	--	°C	
Melting Temperature ³	174	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.4E-4	--	cm/cm/°C	
Transverse	1.6E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+12	ohms	IEC 60093
Volume Resistivity	--	1.0E+13	ohms·cm	IEC 60093
Electric Strength	--	32	kV/mm	IEC 60243-1
Comparative Tracking Index	--	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method

Flammability Classification (0.800 mm)	HB	--	IEC 60695-11-10, -20
Additional Information	Dry	Conditioned	Test Method
ISO Type	PA12-P, GHL, 18-005	--	ISO 1874
NOTE			
1.	Long Term		
2.	Short Term		
3.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT