

Starex GR-4015A

Acrylonitrile Butadiene Styrene

SAMSUNG SDI CO., LTD.

Message:

Starex GR-4015A is an Acrylonitrile Butadiene Styrene (ABS) product filled with glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	7.0	g/10 min	ASTM D1238, ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785, ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield ¹	73.0	MPa	ASTM D638
Yield	72.0	MPa	ISO 527-2/50
Flexural Modulus			
-- ²	5300	MPa	ASTM D790
-- ³	5000	MPa	ISO 178
Flexural Strength			
-- ⁴	98.0	MPa	ASTM D790
-- ⁵	95.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁶ (23°C)	5.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C, 3.18 mm	69	J/m	ASTM D256
23°C ⁷	6.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	102	°C	ASTM D648
Vicat Softening Temperature	106	°C	ISO 306/B50
Flammability	Nominal Value	Test Method	
Flame Rating (1.50 to 1.65 mm)	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature			
--	80.0	°C	
Desiccant Dryer	80.0	°C	
Drying Time			

--	2.0 to 4.0	hr
Desiccant Dryer	2.0 to 3.0	hr
Suggested Max Moisture	< 0.050	%
Rear Temperature	180 to 190	°C
Middle Temperature	200 to 210	°C
Front Temperature	220 to 230	°C
Nozzle Temperature	240	°C
Mold Temperature	40.0 to 80.0	°C
Injection Pressure	49.0 to 245	MPa
Back Pressure	0.490 to 1.96	MPa
Screw Speed	50 to 150	rpm

NOTE

- | | |
|----|-----------------|
| 1. | 5.0 mm/min |
| 2. | 2.8 mm/min |
| 3. | 2.0 mm/min |
| 4. | 2.8 mm/min |
| 5. | 2.0 mm/min |
| 6. | Thickness: 4 mm |
| 7. | Thickness: 4 mm |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

