

Hostaform® C 52021 LS

Polyphenylene Sulfide

Celanese Corporation

Message:

POM copolymer

Extremely easy flowing Injection molding type for very thin-walled precision molded parts with unfavourite flow-path-wallthickness relation; permits processing at reduced temperature and also shorter cycle times; for mechanical lower requirements; good chemical resistance to solvents, fuel and strong alkalis as well as good hydrolysis resistance; high resistance to thermal and oxidative degradation. With UV Additives

Ranges of applications: For very thin-walled precision molded parts with unfavourite flow-path-wallthickness relation; permits processing at reduced temperature and also shorter cycle times.

General Information			
Additive	UV stabilizer		
Features	Copolymer		
	Solvent resistance		
	Fast molding cycle		
	Good liquidity		
	Good chemical resistance		
	alkali resistance		
	Fuel resistance		
	Hydrolysis resistance		
Uses	Thin wall parts		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	39.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Transverse flow	1.8	%	ISO 294-4
Flow	1.9	%	ISO 294-4
Water Absorption (Saturation, 23°C)	0.65	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3000	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	65.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	7.0	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	15	%	ISO 527-2/1A/50
Tensile Creep Modulus			ISO 899-1
1 hr	2500	MPa	ISO 899-1
1000 hr	1300	MPa	ISO 899-1
Flexural Modulus (23°C)	2800	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength			ISO 179/1eA
-30°C	5.0	kJ/m ²	ISO 179/1eA
23°C	5.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	150	kJ/m ²	ISO 179/1eU
23°C	150	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	106	°C	ISO 75-2/A
Melting Temperature ¹	166	°C	ISO 11357-3
CLTE - Flow	1.1E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms · cm	IEC 60093
Dielectric Strength	35	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	4.00		IEC 60250
1 MHz	4.00		IEC 60250
Dissipation Factor			IEC 60250
100 Hz	3.0E-3		IEC 60250
1 MHz	5.0E-3		IEC 60250
Comparative Tracking Index	600	V	IEC 60112
Fill Analysis	Nominal Value	Unit	
Melt Density	1.20	g/cm ³	
Melt Specific Heat	2060	J/kg/°C	
Melt Thermal Conductivity	0.19	W/m/K	
Ejection Temperature	140	°C	
Injection	Nominal Value	Unit	
Drying Temperature	120 - 140	°C	
Drying Time	3.0 - 4.0	hr	
Suggested Max Moisture	0.15	%	
Hopper Temperature	20 - 30	°C	
Rear Temperature	170 - 180	°C	
Middle Temperature	180 - 190	°C	
Front Temperature	190 - 200	°C	
Nozzle Temperature	190 - 210	°C	
Processing (Melt) Temp	190 - 210	°C	
Mold Temperature	80 - 120	°C	
Injection Pressure	60.0 - 120	MPa	
Injection Rate	Slow-Moderate		
Holding Pressure	60.0 - 120	MPa	
Back Pressure	0.00 - 4.00	MPa	

Injection instructions

Manifold Temperature: 190 to 210°C Zone 4 Temperature: 190 to 210°C Feed Temperature: 60 to 80°C

NOTE

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

