

RTP 2720 S-50A

Styrene Ethylene Butylene Styrene Block Copolymer

RTP Company

Message:

RTP 2720 S-50A is a Styrene Ethylene Butylene Styrene Block Copolymer (SEBS) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

General Information			
RoHS Compliance	Contact Manufacturer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	54		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (100% Strain, 3.18 mm)	1.24	MPa	ASTM D412
Tensile Strength ² (Break, 3.20 mm)	9.03	MPa	ASTM D412
Tensile Elongation ³ (Break)	810	%	ASTM D412
Tear Strength ⁴	23.6	kN/m	ASTM D624
Compression Set ⁵			ASTM D395B
23°C, 22 hr	16	%	
70°C, 22 hr	34	%	
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	182 to 232	°C	
Mold Temperature	15.6 to 37.8	°C	
NOTE			
1.	Die C, 510 mm/min		
2.	Die C, 500 mm/min		
3.	Die C, 500 mm/min		
4.	Die C		
5.	Type 2		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

