

TPX® MX004XB

Polymethylpentene Copolymer

Mitsui Chemicals, Inc.

Message:

TPX®MX004XB is a polymethylpentene copolymer (PMP copolymer) material. This product is available in North America. The processing methods are: film extrusion, blow molding, extrusion, fiber (spinning) extrusion or injection molding.

TPX®The main features of the MX004XB are:

chemical resistance

Heat resistance

non-toxic

Typical application areas include:

Movie

food contact applications

medical/health care

General Information			
Features	Good chemical resistance		
	Thermal stability, good		
	Non-toxic		
Uses	Films		
	Medical/nursing supplies		
Agency Ratings	FDA Food Exposure, Not Rated		
	JHOSPA not rated		
Appearance	Transparent-Light Blue		
Forms	Particles		
Processing Method	Film extrusion		
	Blow molding		
	Extrusion		
	Fiber (spinning) extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.833	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	25	g/10 min	ASTM D1238
Spiral Flow ¹	53.0	cm	Internal method
Molding Shrinkage ²			Internal method
Flow	1.5	%	Internal method
Transverse flow	1.1	%	Internal method
Water Absorption (24 hr)	< 0.010	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method

Rockwell Hardness (R-Scale)	75		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	1300	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield, 23°C	25.0	MPa	ASTM D638
Fracture, 23°C	20.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	30	%	ASTM D638
Flexural Modulus (23°C)	1050	MPa	ASTM D790
Flexural Strength (23°C)	32.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	24	J/m	ASTM D256
Unnotched Izod Impact Strength (23°C)	40	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	100	°C	ASTM D648
Vicat Softening Temperature	165	°C	ASTM D1525
Melting Temperature	228	°C	DSC
CLTE - Flow	1.2E-4	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	65	kV/mm	ASTM D149
Dielectric Constant	2.10		ASTM D150
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.460		ASTM D542
Transmittance	94.0	%	ASTM D1003
Haze	0.70	%	ASTM D1003
NOTE			
1.	Mold temperature: 73°C, melt temperature: 310 to 320°C		
2.	temperature range: 260 to 280°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT