

TAROLON 2500 G6 X1

Polycarbonate

Taro Plast S.p.A.

Message:

Polycarbonate medium viscosity, 30% glass fiber reinforced, self extinguishing, brominated flame retardants free, good mechanical properties also at high temperature, good dimensional stability.
UL 94 approved all colors V1 at 1,6 mm and V0 at 3,5 mm.
Available: all colors.

General Information			
UL YellowCard	E143048-312233		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Brominated		
	Good Dimensional Stability		
	Medium Heat Resistance		
	Medium Viscosity		
	Self Extinguishing		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm ³	ASTM D792, ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/2.16 kg)	8.50	cm ³ /10min	ISO 1133
Molding Shrinkage			ASTM D955
Flow	0.15 to 0.20	%	
Across Flow	0.30 to 0.40	%	
Water Absorption			
23°C, 24 hr	0.050	%	ASTM D570, ISO 62
Saturation	0.20	%	ASTM D570
Saturation, 23°C	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8000	MPa	ASTM D638, ISO 527-2
Tensile Strength (Break)	126	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	2.6	%	ASTM D638, ISO 527-2
Flexural Modulus	7800	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ¹ (23°C)	15	kJ/m ²	ASTM D256, ISO 179
Notched Izod Impact (23°C, 3.20 mm)	140	J/m	ISO 180, ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed)	148	°C	ASTM D648, ISO 75-2/A
Continuous Use Temperature			
--	75.0	°C	UL 746B
-- ²	130	°C	IEC 60216
Vicat Softening Temperature	158	°C	ISO 306/A50, ASTM D1525 ³
Ball Pressure Test (135°C)	Pass		VDE 0470
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	150	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-1		
3.50 mm	V-0		
Glow Wire Ignition Temperature (2.00 mm)	960	°C	IEC 60695-2-13
Oxygen Index	36	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature			
--	100 to 110	°C	
Pre-heater	120 to 130	°C	
Drying Time			
--	1.0 to 2.0	hr	
Pre-heater	4.0	hr	
Processing (Melt) Temp	260 to 300	°C	
Mold Temperature	100 to 120	°C	
Injection Rate	Fast		
NOTE			
1.	6x4x50 mm		
2.	20000 hrs		
3.	Rate A (50°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT