

RTP 100 GB 40

Polypropylene
RTP Company

Message:
Glass Bead

General Information			
Filler / Reinforcement	Glass Bead,40% Filler by Weight		
RoHS Compliance	Contact Manufacturer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	1.0 to 1.5	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2620	MPa	ASTM D638
Tensile Strength	20.0	MPa	ASTM D638
Tensile Elongation (Yield)	> 10	%	ASTM D638
Flexural Modulus	2210	MPa	ASTM D790
Flexural Strength	35.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	37	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	370	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	73.9	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm, ** Values per RTP Company testing.)	HB		UL 94
Additional Information	Nominal Value	Unit	
Primary Additive	40	%	
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	191 to 232	°C	
Mold Temperature	32.2 to 65.6	°C	
Injection Pressure	68.9 to 103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

