

DINALON® B1S25 MI

Polyamide 6

Grupo Repol

Message:

DINALON® B1S25 MI is a Polyamide 6 (Nylon 6) product. It is available in Europe. Primary characteristic: impact resistant.

General Information			
Features	Medium Impact Resistance		
Appearance	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183/A
Humidity ¹	< 0.25	%	ISO 15512/B
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2
Tensile Stress (Break)	65.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	4.0	%	
Break	> 25	%	
Flexural Modulus	1800	MPa	ISO 178
Flexural Stress	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	17	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	55.0	°C	ISO 75-2/A
Vicat Softening Temperature	> 200	°C	ISO 306/B
NOTE			
1.	Karl-Fischer		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT