

OnFlex™ S KE 70A-3E1726 SO10

Thermoplastic Elastomer

PolyOne Corporation

Message:

OnFlex™-S KE thermoplastic elastomer polymer is mixed with hydrogenated styrene block copolymer. This series of polymers has good compatibility and can provide excellent adhesion to a variety of polar substrates, such as PC, ABS, PC/ABS, ASA, and PVC materials. OnFlex-S KE polymer can be processed by 2K molding or multiple injection molding, plug-in molding or co-extrusion. In addition, OnFlex-S KE polymer has good compression set even at high temperatures, good processability, large hardness range, good bending, scratch resistance, colorability, surface appearance, etc. at low temperatures, and excellent mechanical properties.

General Information			
Features	Good UV resistance		
	Good adhesion		
	Scratch resistance		
	Good demoulding performance		
Uses	overmolding		
	Power/other tools		
	Industrial application		
	Application in Automobile Field		
	Consumer goods application field		
RoHS Compliance	RoHS compliance		
Appearance	Black		
Forms	Particle		
Processing Method	Multiple injection molding		
	Co-extrusion molding		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	70		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% strain	3.00	MPa	ISO 37
300% strain	5.80	MPa	ISO 37
Tensile Stress (Break)	11.3	MPa	ISO 37
Tensile Elongation (Break)	500	%	ISO 37
Compression Set			ISO 815
23°C, 72 hr	29	%	ISO 815
70°C, 22 hr	50	%	ISO 815

100°C, 22 hr	73	%	ISO 815
Additional Information	Nominal Value		
General Material Type	Styrene thermoplastic elastomers (TES)		
各项属性值是采用注射模制基板测量得出.压缩永久变形值是 100°C 时 24 小时零件变形实验得出的值.			
Injection	Nominal Value	Unit	
Drying Temperature	100	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	200 - 230	°C	
Mold Temperature	20.0 - 40.0	°C	
Injection Rate	Slow-Moderate		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

