

Durethan® B 30 S FN30 000000

Polyamide 6

LANXESS GmbH

Message:

PA 6, non-reinforced, injection molding, halogen free flame retardant, heat-aging resistance

General Information				
UL YellowCard		E245249-100915707		
Additive		Flame Retardant		
Features		Flame Retardant		
		Halogen Free		
		Heat Stabilized		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.14	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Across Flow : 260°C, 2.00 mm ¹	0.90	--	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.30	--	%	
Flow : 260°C, 2.00 mm ³	0.90	--	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.30	--	%	
Water Absorption				ISO 62
Saturation, 23°C	9.0	--	%	
Equilibrium, 23°C, 50% RH	2.6	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	3700	1200	MPa	ISO 527-2/1
Tensile Stress				
Yield, 23°C	80.0	40.0	MPa	ISO 527-2/50
Break, 23°C	80.0	50.0	MPa	ISO 527-2/5
Tensile Strain				
Yield, 23°C	3.5	20	%	ISO 527-2/50
Break, 23°C	14	> 50	%	ISO 527-2/5
Nominal Tensile Strain at Break (23°C)	10	> 50	%	ISO 527-2/50
Flexural Modulus ⁵ (23°C)	3600	1200	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% Strain,23°C	110	35.0	MPa	
23°C ⁶	120	45.0	MPa	

Flexural Strain at Flexural Strength ⁷ (23°C)	5.5	8.0	%	ISO 178/A
ISO Shortname	PA 6, GFHR, 12-030; ISO 1043-PA FR (30)			ISO 1874
Residual Moisture Content	0.030 to 0.070			Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	< 10	15	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	75	75	kJ/m ²	
23°C	90 kJ/m ²	No Break		
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	65	85	kJ/m ²	
23°C	90 kJ/m ²	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	185	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	65.0	--	°C	ISO 75-2/A
Ball Pressure Test (207°C)	Pass	--		IEC 60695-10-2
Melting Temperature ⁸	222	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	7.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	8.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+16	--	ohms	IEC 60167
Volume Resistivity (23°C)	1.0E+15	--	ohms·cm	IEC 60093
Electric Strength (23°C, 1.00 mm)	31	--	kV/mm	IEC 60243-1
Comparative Tracking Index (CTI)	PLC 0	--		UL 746
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.380 mm	V-0	--		
0.750 mm	V-0	--		
1.50 mm	V-0	--		
3.00 mm	V-0	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.400 mm	960	--	°C	
0.800 mm	960	--	°C	
1.50 mm	960	--	°C	
3.00 mm	960	--	°C	

Glow Wire Ignition Temperature				IEC 60695-2-13
0.400 mm	775	--	°C	
0.800 mm	775	--	°C	
1.50 mm	775	--	°C	
Oxygen Index ⁹	40	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	250 to 270		°C	
Mold Temperature	80.0 to 100		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	2 mm/min			
8.	10°C/min			
9.	Procedure A			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

