

SABIC® STAMAX 30YM240E

Polypropylene

Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® STAMAX 30YM240E is a 30% long glass fiber reinforced low emission grade. The glass fibres are chemically coupled to the PP matrix, resulting in high stiffness and strength.

General Information			
Filler / Reinforcement	Long Glass Fiber,30% Filler by Weight		
Features	Chemically Coupled		
	High Stiffness		
	High Strength		
	Low Emissions		
Uses	Automotive Applications		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-2/1B
23°C, Injection Molded	6650	MPa	
80°C, Injection Molded	4600	MPa	
120°C, Injection Molded	3500	MPa	
Tensile Stress ¹			ISO 527-2
23°C, Injection Molded	110	MPa	
80°C, Injection Molded	70.0	MPa	
120°C, Injection Molded	51.0	MPa	
Tensile Strain (Break, 23°C, Injection Molded)	2.3	%	ISO 527-2/1B
Flexural Modulus			ISO 178
23°C, Injection Molded	5900	MPa	
80°C, Injection Molded	4200	MPa	
Flexural Stress			ISO 178
23°C, Injection Molded	147	MPa	
80°C, Injection Molded	86.0	MPa	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C, Injection Molded	25	kJ/m ²	
23°C, Injection Molded	19	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU

-30°C, Injection Molded	36	kJ/m²	
23°C, Injection Molded	52	kJ/m²	
Falling Dart Impact - Total Energy ² (23°C)	58.0	J/cm	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	156	°C	ISO 75-2/A
CLTE - Flow			ASTM D696
-30 to 30°C	5.1E-5	cm/cm/°C	
23 to 80°C	4.1E-5	cm/cm/°C	
NOTE			
1.	Type 1B		
2.	Injection Molded		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

