

Telcar® TL-1522B

Thermoplastic Elastomer

Teknor Apex Company

Message:

Telcar®TL-1522B is a thermoplastic elastomer (TPE) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is extrusion or injection molding.

Typical application areas include:

Automotive Industry
engineering/industrial accessories

General Information			
Uses	Blow molding applications		
	Washer		
	Weather-resistant sealing strip		
	Application in Automobile Field		
	Car interior parts		
	Automotive exterior parts		
	Car exterior decoration		
	General		
Appearance	Opacity		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	85	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	40		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance			ASTM D2228
1000 Cycles, 1000g, H-18 wheel	1610	mg	ASTM D2228
1000 Cycles, 1000g, H-22 wheel	2130	mg	ASTM D2228
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain	1.38	MPa	ASTM D412
300% strain	2.14	MPa	ASTM D412
Tensile Strength (Break)	3.45	MPa	ASTM D412
Tensile Elongation (Break)	510	%	ASTM D412
Tear Strength ¹	12.4	kN/m	ASTM D1004

Compression Set			ASTM D395
23°C, 22 hr	25	%	ASTM D395
70°C, 22 hr	72	%	ASTM D395
100°C, 22 hr	97	%	ASTM D395
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity			ASTM D257
23°C	6.2E+15	ohms·cm	ASTM D257
50°C	6.2E+13	ohms·cm	ASTM D257
Dielectric Strength	31	kV/mm	ASTM D149
Injection	Nominal Value	Unit	
Rear Temperature	171 - 193	°C	
Middle Temperature	177 - 199	°C	
Front Temperature	182 - 204	°C	
Nozzle Temperature	188 - 210	°C	
Processing (Melt) Temp	188 - 210	°C	
Mold Temperature	25.0 - 65.6	°C	
Injection Pressure	1.38 - 6.89	MPa	
Injection Rate	Moderate-Fast		
Back Pressure	0.172 - 0.345	MPa	
Screw Speed	50 - 100	rpm	
Cushion	3.81 - 25.4	mm	
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	166 - 188	°C	
Cylinder Zone 2 Temp.	171 - 193	°C	
Cylinder Zone 3 Temp.	177 - 199	°C	
Cylinder Zone 5 Temp.	182 - 204	°C	
Die Temperature	190 - 210	°C	
Extrusion instructions			
螺杆转速30 - 100 rpm			
NOTE			
1.	C mould		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT