

LNP™ VERTON™ MV006S compound

Polypropylene

SABIC Innovative Plastics

Message:

LNP VERTON MV006S is a compound based on Polypropylene resin containing 30% Long Glass Fiber. Added features of this material include: Chemically Coupled, Structural.

Also known as: LNP* VERTON* Compound MFX-7006 HS

Product reorder name: MV006S

General Information			
UL YellowCard	E121562-101358099		
Filler / Reinforcement	Long Glass Fiber,30% Filler by Weight		
Features	Chemically Coupled		
Uses	Structural Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.13	g/cm ³	ASTM D792
--	1.12	g/cm ³	ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.30	%	ASTM D955
Across Flow : 24 hr	0.60	%	ASTM D955
Across Flow : 24 hr	0.59	%	ISO 294-4
Flow : 24 hr	0.27	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7810	MPa	ISO 527-2/1
Tensile Strength			
Break	103	MPa	ASTM D638
Break	105	MPa	ISO 527-2
Tensile Elongation (Break)	2.6	%	ASTM D638, ISO 527-2
Flexural Modulus			
--	6030	MPa	ASTM D790
--	6450	MPa	ISO 178
Flexural Strength			
--	150	MPa	ASTM D790
--	153	MPa	ISO 178
Coefficient of Friction			
vs. Itself - Dynamic	0.36		
vs. Itself - Static	0.39		
Wear Factor - Washer	44.0	10 ⁻¹⁰ in ⁴ 5-min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact			
23°C	160	J/m	ASTM D256
23°C ¹	19	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	770	J/m	ASTM D4812
23°C ²	50	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	10.0	J	ASTM D3763
--	10.0	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ³ (1.8 MPa, Unannealed, 64.0 mm Span)	158	°C	ISO 75-2/Af
CLTE			ASTM E831
Flow : -40 to 40°C	1.8E-5	cm/cm/°C	
Transverse : -40 to 40°C	4.5E-5	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Rear Temperature	232 to 243	°C	
Middle Temperature	243 to 254	°C	
Front Temperature	249 to 260	°C	
Processing (Melt) Temp	221 to 249	°C	
Mold Temperature	37.8 to 65.6	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	80*10*4		
2.	80*10*4		
3.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT