

# G-Lene E36A060

Linear Low Density Polyethylene

Gas Authority of India Limited

Message:

E36A060 has excellent process ability and is suitable for coating/lamination of Woven Bags, Tarpaulin etc.

| General Information                       |                                     |                   |             |
|---|-------------------------------------|-------------------|-------------|
| Additive                                  | Antioxidant                         |                   |             |
| Features                                  | Antioxidant                         |                   |             |
|   | High Gloss                          |                   |             |
|   | High Impact Resistance              |                   |             |
|   | High Stiffness                      |                   |             |
|   | Low Gel                             |                   |             |
|   | Low Warpage                         |                   |             |
|   | Med.-Wide Molecular Weight Distrib. |                   |             |
| Uses                                      | Coating Applications                |                   |             |
|   | Fabric Coatings                     |                   |             |
| Forms                                     | Pellets                             |                   |             |
| Processing Method                         | Extrusion Coating                   |                   |             |
| Physical                                  | Nominal Value                       | Unit              | Test Method |
| Density                                   | 0.932                               | g/cm <sup>3</sup> | ASTM D1505  |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 kg) | 6.0                                 | g/10 min          | ASTM D1238  |
| Thermal                                   | Nominal Value                       | Unit              | Test Method |
| Vicat Softening Temperature               | 118                                 | °C                | ASTM D1525  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT