

Kumho ABS 740

Acrylonitrile Butadiene Styrene
Korea Kumho Petrochemical Co., Ltd.

Message:

Features: High impact resistance
Applications: Automobile parts(radiator grill etc), Helmets, Toys

General Information			
UL YellowCard	E65424-247677		
Features	High Heat Resistance		
Uses	Automotive Applications		
	Toys		
RoHS Compliance	RoHS Compliant		
UL File Number	E65424		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			
200°C/21.6 kg	35	g/10 min	ASTM D1238
220°C/10.0 kg	25	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow	0.50 to 0.80	%	ASTM D955
--	0.50 to 0.80	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	98		ASTM D785, ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield	41.2	MPa	ASTM D638
Yield	40.0	MPa	ISO 527-2
Tensile Elongation			
Yield	25	%	ASTM D638
Break	27	%	ISO 527-2
Flexural Modulus			
--	1960	MPa	ASTM D790
--	2000	MPa	ISO 178
Flexural Stress			
--	59.0	MPa	ISO 178
Yield	56.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	32	kJ/m ²	ISO 179/1eA

Notched Izod Impact			
23°C, 3.20 mm	350	J/m	ASTM D256
23°C, 6.40 mm	290	J/m	ASTM D256
23°C	31	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	90.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	84.0	°C	ASTM D648
1.8 MPa, Unannealed	79.0	°C	ISO 75-2/A
Vicat Softening Temperature	94.0	°C	ISO 306/B50, ASTM D1525 1
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
NOTE			

1. Rate A (50°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

