

Lupoy® SC1004ML

Polycarbonate

LG Chem Ltd.

Message:

Description

General Purpose, High Impact, Good Coloring, Chemical Resistance

Application

Mobile Phone Housing

General Information			
UL YellowCard	E302314-530035	E67171-318084	E248280-533907
Features	General Purpose		
	Good Chemical Resistance		
	Good Colorability		
	High Impact Resistance		
Uses	Cell Phones		
	Electrical/Electronic Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.80	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	117		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	56.9	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	130	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	2160	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 3.20 mm)	88.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm	290	J/m	
23°C, 3.20 mm	690	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ⁵ (0.45 MPa, Unannealed, 6.40 mm)	130	°C	ASTM D648
RTI Elec	80.0	°C	UL 746
RTI Imp	80.0	°C	UL 746
RTI Str	80.0	°C	UL 746

Flammability	Nominal Value	Test Method
Flame Rating (0.700 mm)	HB	UL 94

Injection	Nominal Value	Unit
Drying Temperature	100 to 110	°C
Drying Time	3.0 to 5.0	hr
Suggested Max Moisture	< 0.020	%
Rear Temperature	275 to 290	°C
Middle Temperature	285 to 305	°C
Front Temperature	290 to 310	°C
Nozzle Temperature	285 to 305	°C
Processing (Melt) Temp	290 to 310	°C
Mold Temperature	80.0 to 110	°C
Back Pressure	0.981 to 3.92	MPa
Screw Speed	40 to 70	rpm

NOTE		
1.	50 mm/min	
2.	50 mm/min	
3.	10 mm/min	
4.	10 mm/min	
5.	18.6kg	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

