

VESTAMID® Care ME40

Polyether Block Amide

Evonik Industries AG

Message:

VESTAMID® Care ME grades represent a range of flexible polyether block amide (PEBA) resins of varying hardness for processing via extrusion or injection molding. VESTAMID® Care ME materials are available as standard and bonding-modified grades.

VESTAMID® Care ME standard grades have a proven history in catheter applications. Due to their broad range of flexibility, VESTAMID® CareME grades are used in different parts of catheter constructions - may it be the distal end, requiring a low modulus for non-traumatic insertion, or the proximal end, needing a high modulus for force and torque transmission. The advantages at a glance:

- High flexibility & elasticity
- Good rebound properties
- High impact resistance
- High dimensional stability
- High chemical resistance
- High toughness
- Easy processability & colorability
- Free of volatile plasticizers

| General Information | | | |
|-----------------------|---------------------------------|-------|-------------|
| Features | Biocompatible | | |
| | Good Chemical Resistance | | |
| | Good Colorability | | |
| | Good Dimensional Stability | | |
| | Good Flexibility | | |
| | Good Processability | | |
| | Good Toughness | | |
| | High Elasticity | | |
| | High Impact Resistance | | |
| | | | |
| Uses | Medical Devices | | |
| | Medical/Healthcare Applications | | |
| | Tubing | | |
| Agency Ratings | ISO 10993 | | |
| | USP 88 | | |
| | USP Class VI | | |
| Processing Method | Extrusion | | |
| | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density (23°C) | 1.01 | g/cm³ | ISO 1183 |
| Molding Shrinkage | | | ISO 294-4 |
| Across Flow : 3.00 mm | 0.70 to 1.3 | % | |

| | | | |
|--|----------------------|-------------|--------------------|
| Flow : 3.00 mm | 0.60 to 0.90 | % | |
| Water Absorption (Saturation, 23°C) | 1.0 | % | ISO 62 |
| Hardness | Nominal Value | Unit | Test Method |
| Shore Hardness (Shore D) | 40 | | ISO 868 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 80.0 | MPa | ISO 527-2 |
| Tensile Stress | | | ISO 527-2/50 |
| Yield, 23°C | 17.0 | MPa | |
| 50% Strain, 23°C | 9.50 | MPa | |
| Tensile Strain (Break, 23°C) | > 200 | % | ISO 527-2/50 |
| Tensile Creep Modulus (1000 hr) | 60.0 | MPa | ISO 899-1 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Notched Impact Strength | | | ISO 179/1eA |
| -30°C | No Break | | |
| 23°C | No Break | | |
| Charpy Unnotched Impact Strength | | | ISO 179/1eU |
| -30°C | No Break | | |
| 23°C | No Break | | |
| Thermal | Nominal Value | Unit | Test Method |
| Heat Deflection Temperature (0.45 MPa, Unannealed) | 55.0 | °C | ISO 75-2/B |
| Vicat Softening Temperature | | | |
| -- | 125 | °C | ISO 306/A |
| -- | 60.0 | °C | ISO 306/B |
| CLTE | | | ISO 11359-2 |
| Flow : 23 to 55°C | 2.4E-4 | cm/cm/°C | |
| Transverse : 23 to 55°C | 2.1E-4 | cm/cm/°C | |
| Flammability | Nominal Value | | Test Method |
| Flame Rating (1.60 mm) | HB | | UL 94 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT