

TPX® MX002

Polymethylpentene Copolymer
Mitsui Chemicals America, Inc.

Message:

TPX®MX002 is a polymethylpentene copolymer (PMP copolymer) material. This product is available in Europe or the Asia-Pacific region. The processing methods are: blow molding, extrusion or injection molding. TPX®The main characteristics of MX002 are: hardness.

General Information			
Features	Semi Rigid		
Forms	Particle		
Processing Method	Blow molding		
	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.835	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR)	21	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	1.6	%	ASTM D955
Transverse flow	1.6	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	62		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	785	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield, 23°C	20.0	MPa	ASTM D638
23°C	20.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	60	%	ASTM D638
Flexural Modulus (23°C)	641	MPa	ASTM D790
Flexural Strength (23°C)	24.8	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	75.0	°C	ASTM D648
Vicat Softening Temperature	151	°C	ASTM D1525
Melting Temperature	222	°C	
CLTE - Flow	3.8E-4	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Strength	63	kV/mm	ASTM D149
Dielectric Constant	2.12		ASTM D150
Optical	Nominal Value	Unit	Test Method

Refractive Index	1.463	ASTM D542
Clarity	93.0	ASTM D1746
Haze	0.90	% ASTM D1003

Additional Information

Unnotched Izod Impact, ASTM D256, 23°C: 98 kJ/m²

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

