

Alcryn® 2360 BK

Melt Processable Rubber

Advanced Polymer Alloys

Message:

Alcryn® 2360 BK is a Melt Processable Rubber (MPR) material. It is available in Asia Pacific, Europe, or North America.

Important attributes of Alcryn® 2360 BK are:

RoHS Compliant

WEEE Compliant

General Information			
Agency Ratings	EU 2002/96/EC (WEEE)		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792, ISO 1183
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	62		ASTM D2240, ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Set	9	%	ASTM D412
Tensile Stress (100% Strain)	2.69	MPa	ASTM D412, ISO 37
Tensile Strength (Yield)	8.96	MPa	ASTM D412, ISO 37
Tensile Elongation (Break)	420	%	ASTM D412, ISO 37
Tear Strength			
24°C ¹	26.3	kN/m	ASTM D624
24°C	26	kN/m	ISO 34-1
Compression Set			
24°C, 22 hr	14	%	ASTM D395A
100°C, 22 hr	65	%	ASTM D395A
24°C, 22 hr ²	14	%	ISO 815
100°C, 22 hr ³	65	%	ISO 815
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air			
125°C, 168 hr	90	%	ASTM D573, ISO 188
100% Strain, 125°C, 168 hr	93	%	ASTM D573
100% Strain 125°C, 168 hr	93	%	ISO 188
Change in Volume			
100°C, 168 hr, in ASTM Oil #1	3.0	%	ASTM D471
100°C, 168 hr, in IRM 903 Oil #3	12	%	ASTM D471
100°C, 168 hr, in Water	-22	%	ASTM D471, ISO 1817
100°C, 168 hr, in ASTM #1 Oil	3.0	%	ISO 1817

100°C, 56640 hr, in IRM 903 Oil #3	12	%	ISO 1817
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (190°C, 300 sec ⁻¹)	290	Pa·s	ASTM D3835
Injection	Nominal Value	Unit	
Processing (Melt) Temp	177	°C	
NOTE			
1.	Die C		
2.	Type A		
3.	Type A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

