

LNP™ THERMOTUF™ DF008EI compound

Polycarbonate
SABIC Innovative Plastics

Message:

LNP THERMOTUF DF008EI is a compound based on Polycarbonate resin containing Glass Fiber. Added features of this material include: Easy Molding, Mold Release, High Impact.

Also known as: LNP* THERMOTUF* Compound DF-1008 EM HI MR

Product reorder name: DF008EI

General Information			
UL YellowCard	E207780-101345229		
Filler / Reinforcement	Glass fiber reinforced material		
Additive	demoulding		
Features	Impact resistance, high		
	Good formability		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.51	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Transverse flow: 24 hours	0.30	%	ASTM D955
Vertical flow direction: 24 hours	0.33	%	ISO 294-4
Flow direction: 24 hours	0.040	%	ISO 294-4

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	12600	MPa	ASTM D638
--	11100	MPa	ISO 527-2/1
Tensile Strength			
Yield	132	MPa	ASTM D638
Yield	129	MPa	ISO 527-2
Fracture	132	MPa	ASTM D638
Fracture	130	MPa	ISO 527-2
Tensile Elongation			
Yield	2.2	%	ASTM D638
Yield	2.0	%	ISO 527-2
Fracture	2.2	%	ASTM D638
Fracture	2.0	%	ISO 527-2
Flexural Modulus			
--	10600	MPa	ASTM D790
--	10100	MPa	ISO 178
Flexural Strength			
--	200	MPa	ASTM D790

--	140	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	160	J/m	ASTM D256
23°C ²	17	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	840	J/m	ASTM D4812
23°C ³	52	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	23.1	J	ASTM D3763
--	7.69	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	134	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁴	135	°C	ISO 75-2/Af
Linear thermal expansion coefficient			
Flow: -40 to 40°C	2.5E-5	cm/cm/°C	ASTM E831
Flow: -40 to 40°C	2.7E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	4.1E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	4.3E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value		Test Method
Flame Rating (0.400 mm)	HB		UL 94
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT