

Next PC CX-01BK

Polycarbonate

Next Polymers Ltd.

Message:

Description
PC UnFilled Black Compound

Product Applications
Electrical/Electronics, Housing Appliance, Industrial, Medical & health care application such as Telecommunication hardware, sunroom, carports, car & truck washes, LCD, sliding doors, window, lab Instrument etc

Benefits
Good dimensional stability & High heat resistance

General Information			
Features	Good Dimensional Stability		
	High Heat Resistance		
Uses	Electrical/Electronic Applications		
	Housings		
	Industrial Applications		
	Medical/Healthcare Applications		
	Telecommunications		
	Windows & Doors		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	0.50	%	
Across Flow	0.50	%	
Water Absorption			ASTM D570
23°C, 24 hr	0.30	%	
Saturation ¹	0.35	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ASTM D638
Tensile Strength	62.0	MPa	ASTM D638
Tensile Elongation (Break)	> 70	%	ASTM D638

Flexural Modulus	2300	MPa	ASTM D790
Flexural Strength	92.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area)			ASTM D256
-30°C	12.0	kJ/m ²	
23°C	65.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	136	°C	
1.8 MPa, Unannealed	125	°C	
Vicat Softening Temperature	140	°C	ASTM D1525
CLTE - Flow (23 to 80°C)	7.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.20	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Electric Strength	30	kV/mm	IEC 60243-1
Dielectric Constant (60 Hz)	3.00		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-2		UL 94
Injection	Nominal Value	Unit	
Drying Temperature - Hot Air Dryer	120	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	270 to 280	°C	
Middle Temperature	280 to 290	°C	
Front Temperature	290 to 300	°C	
Mold Temperature	80.0 to 110	°C	
NOTE			
1.	Immersed		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 1342475533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT