

VECTRA® E150i

Liquid Crystal Polymer
Celanese Corporation

Message:

Easy flowing grade with very good heat resistance, and mechanical properties. May reduce warpage in some parts compared to E130i. 50% glass reinforced.

Chemical abbreviation according to ISO 1043-1 : LCP

Inherently flame retardant

FDA compliant

UL-Listing V-0 in natural and black at 0.43mm thickness per UL 94 flame testing.

Relative-Temperature-Index (RTI) according to UL 746B: electricals 240°C, mechanicals 240°C at 0.75mm.

UL = Underwriters Laboratories (USA)

General Information			
UL YellowCard	E83005-251023		
Filler / Reinforcement	Glass fiber reinforced material, 50% filler by weight		
Features	Halogen-free		
	Flame retardancy		
Agency Ratings	EU 2002/96/EC (WEEE)		
RoHS Compliance	Contact manufacturer		
Forms	Particle		
Processing Method	Injection molding		
Resin ID (ISO 1043)	LCP		
Physical	Nominal Value	Unit	Test Method
Density	1.81	g/cm³	ISO 1183
Molding Shrinkage			ISO 294-4
Vertical flow direction	0.50	%	ISO 294-4
Flow direction	0.20	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	6.0E-3	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	66		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	17500	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	130	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	1.0	%	ISO 527-2/1A/5
Flexural Modulus (23°C)	18600	MPa	ISO 178
Flexural Stress (23°C)	205	MPa	ISO 178
Compressive Modulus	18000	MPa	ISO 604
Compressive Stress (1% Strain)	125	MPa	ISO 604
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m²	ISO 179/1eA

Charpy Unnotched Impact Strength (23°C)	19	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)	12	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	16	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
1.8 MPa, not annealed	260	°C	ISO 75-2/A
8.0 MPa, not annealed	225	°C	ISO 75-2/C
Vicat Softening Temperature	200	°C	ISO 306/B50
Melting Temperature ¹	335	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow	6.0E-6	cm/cm/°C	ISO 11359-2
Lateral	1.7E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Dielectric Strength	28	kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	4.70		IEC 60250
Dissipation Factor (1 MHz)	0.028		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.430 mm	V-0		UL 94
1.50 mm	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	150	°C	
Drying Time	6.0	hr	
Suggested Max Moisture	0.010	%	
Hopper Temperature	20.0 - 30.0	°C	
Rear Temperature	315 - 325	°C	
Middle Temperature	320 - 330	°C	
Front Temperature	325 - 335	°C	
Nozzle Temperature	335 - 345	°C	
Processing (Melt) Temp	335 - 345	°C	
Mold Temperature	80.0 - 120	°C	
Injection Pressure	50.0 - 150	MPa	
Injection Rate	Fast		
Holding Pressure	50.0 - 150	MPa	
Back Pressure	0.00 - 3.00	MPa	
Injection instructions			
Manifold Temperature: 335 to 345°CZone 4 Temperature: 330 to 340°CFeed Temperature: 60 to 80°C			
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

