

LEXAN™ HFD1930 resin

Polycarbonate

SABIC Innovative Plastics

Message:

55 MFR LEXAN High Flow Ductile Copolymer, Natural color only

General Information			
UL YellowCard	E121562-101013732		
Features	Copolymer		
	Ductile		
	High Flow		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	55	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	51.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	0.30	%	
Equilibrium, 23°C, 50% RH	0.15	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2300	MPa	ASTM D638
--	2200	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	60.0	MPa	ASTM D638
Yield	61.0	MPa	ISO 527-2/50
Break ³	57.0	MPa	ASTM D638
Break	56.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	5.5	%	ASTM D638
Yield	6.0	%	ISO 527-2/50
Break ⁵	110	%	ASTM D638
Break	100	%	ISO 527-2/50
Flexural Modulus			

50.0 mm Span ⁶	2280	MPa	ASTM D790
-- ⁷	2200	MPa	ISO 178
Flexural Stress			
--	90.0	MPa	ISO 178
Yield, 50.0 mm Span ⁸	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	11	kJ/m ²	
23°C	60	kJ/m ²	
Charpy Unnotched Impact Strength ¹⁰			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Notched Izod Impact			
-30°C	110	J/m	ASTM D256
0°C	330	J/m	ASTM D256
23°C	670	J/m	ASTM D256
-30°C ¹¹	10	kJ/m ²	ISO 180/1A
23°C ¹²	55	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ¹³			ISO 180/1U
-30°C	No Break		
23°C	No Break		
Instrumented Dart Impact			
23°C, Total Energy	56.0	J	ASTM D3763
--	92.0	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	124	°C	ASTM D648
1.8 MPa, Unannealed, 3.20 mm	110	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹⁴	120	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	141	°C	ASTM D1525 ¹⁵
--	135	°C	ISO 306/B50
--	136	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	8.0E-5	cm/cm/°C	
Transverse : -40 to 40°C	8.0E-5	cm/cm/°C	
Flammability	Nominal Value		Test Method
Flame Rating (0.300 mm)	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.582		ASTM D542
Transmittance (2540 µm)	88.0	%	ASTM D1003

Haze (2540 μm)	< 1.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	104 to 110	°C	
Drying Time	3.0 to 4.0	hr	
Drying Time, Maximum	24	hr	
Suggested Shot Size	40 to 60	%	
Rear Temperature	238 to 282	°C	
Middle Temperature	249 to 293	°C	
Front Temperature	260 to 304	°C	
Nozzle Temperature	254 to 299	°C	
Processing (Melt) Temp	260 to 304	°C	
Mold Temperature	48.9 to 82.2	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	35 to 75	rpm	
Vent Depth	0.038 to 0.076	mm	

NOTE		
1.	5.0 mm/min	
2.	Type I, 50 mm/min	
3.	Type I, 50 mm/min	
4.	Type I, 50 mm/min	
5.	Type I, 50 mm/min	
6.	1.3 mm/min	
7.	2.0 mm/min	
8.	1.3 mm/min	
9.	80*10*3 sp=62mm	
10.	80*10*3 sp=62mm	
11.	80*10*3	
12.	80*10*3	
13.	80*10*3	
14.	80*10*4 mm	
15.	Rate B (120°C/h), Loading 2 (50 N)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT