

ALCOM® MED PS 1000 AS 14114

High Impact Polystyrene

ALBIS PLASTIC GmbH

Message:

ALCOM® MED PS 1000 AS 14114 is a high impact polystyrene product. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region. ALCOM® MED PS 1000 AS 14114 applications include medical/health care and housing.

Features include:

Comply with REACH standard

ROHS certification

Antistatic

General Information			
Additive	Antistatic property		
Features	Antistatic property		
Uses	Personal care Shell Medical/nursing supplies		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (200°C/5.0 kg)	20.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2200	MPa	ISO 527-2
Tensile Stress (Break)	25.0	MPa	ISO 527-2
Tensile Strain (Break)	25	%	ISO 527-2
Flexural Modulus	2100	MPa	ISO 178
Flexural Stress	38.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	69.0	°C	ISO 75-2/A
Vicat Softening Temperature	77.0	°C	ISO 306/B50
Injection	Nominal Value	Unit	Test Method
Drying Temperature			
Dehumidification desiccant	60 - 80	°C	
Hot air dryer	60 - 80	°C	

Drying Time		
Dehumidification desiccant	2.0 - 3.0	hr
Hot air dryer	2.0 - 3.0	hr
Processing (Melt) Temp	180 - 260	°C
Mold Temperature	10 - 70	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

