

ELASTOSIL® R 701/70

Silicone
Wacker Chemie AG

Message:

- Silicone Rubber, HTV
- Molded Parts, Technical, Plastics and Rubber Processing
- Molded Seals, Plastics and Rubber Processing
- Molded Parts, Automotive, Plastics and Rubber Processing
- Membranes, Plastics and Rubber Processing
- Photocopier Rolls, Printing Industry
- Membranes, Automotive & Transportation

General Information			
Features	Grease Resistant		
	Low Compression Set		
	Oil Resistant		
Uses	Automotive Applications		
	Automotive Under the Hood		
	Compounding		
	Gaskets		
	Seals		
Processing Method	Calendering		
	Compression Molding		
	Press Molding		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Beige		
Density	1.29	g/cm³	ISO 1183
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	69		DIN 53505
Tensile Strength	7.80	MPa	DIN 53504
Tensile Elongation at Break	310	%	DIN 53504
Compression Set	10	%	DIN ISO 815-B
Rebound Resilience	50	%	DIN 53512

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

