

VESTOSINT® 2159 natural color

Polyamide 12

Evonik Industries AG

Message:

Powder for coating systems, composites, electrostatic coatings

VESTOSINT 2159 is a polyamide 12 fine powder for the use in liquid coating systems. It is used as an additive, for instance, in coil-coating systems, to improve abrasion resistance and flexibility.

General Information			
Uses	Coating Applications		
	Protective Coatings		
Appearance	Natural Color		
Forms	Powder		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.02	g/cm ³	ISO 1183
Apparent Density	> 0.18	g/cm ³	ISO 60
Water Absorption			ISO 62
Saturation, 100°C ¹	1.9	%	
Saturation, 23°C ²	1.3	%	
Equilibrium, 23°C, 50% RH	0.50	%	
Average Particle Size ³	10	µm	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	75		ISO 868
Ball Indentation Hardness ⁴	90.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	43.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	6.0	%	
Break	> 100	%	
Taber Abrasion Resistance (100 Cycles, 500 g, CS-17 Wheel)	< 1.00	mg	ASTM D1242
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	184	°C	ISO 3146
CLTE - Flow (23 to 55°C)	1.1E-4	cm/cm/°C	ISO 11359-2
Specific Heat	2350	J/kg/°C	DIN 53765
Thermal Conductivity	0.23 to 0.29	W/m/K	DIN 52612
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	IEC 60093
Electric Strength ⁵	90	kV/mm	IEC 60243-1
NOTE			

1.	Immersion
2.	96%RH
3.	Laser diffraction analysis (Sympatec Helos), d50
4.	H30
5.	K20/P50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

