

ALCOM® POM 770/1 SLBV

Acetal (POM) Copolymer

ALBIS PLASTIC GmbH

Message:

ALCOM® POM 770/1 SLBV is an Acetal (POM) Copolymer product. It is available in Asia Pacific, Europe, or North America. Applications of ALCOM® POM 770/1 SLBV include automotive and engineering/industrial parts.

Characteristics include:

REACH Compliant

RoHS Compliant

Copolymer

Heat Stabilizer

Wear Resistant

General Information			
Additive	Heat Stabilizer		
Features	Copolymer		
	Good Wear Resistance		
	Heat Stabilized		
Uses	Automotive Applications		
	Machine/Mechanical Parts		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	8.00	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2600	MPa	ISO 527-2
Tensile Stress	60.0	MPa	ISO 527-2
Tensile Strain (Break)	30	%	ISO 527-2
Flexural Modulus	2450	MPa	ISO 178
Flexural Stress	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
--	8.0	kJ/m ²	
-40°C	6.0	kJ/m ²	
-20°C	6.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
--	No Break		
-40°C	No Break		
-20°C	No Break		

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	105	°C	ISO 75-2/A
Vicat Softening Temperature	145	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature			
Circulation Dryer	100 to 110	°C	
Desiccant Dryer	100 to 110	°C	
Drying Time			
Circulation Dryer	3.0 to 5.0	hr	
Desiccant Dryer	2.0 to 3.0	hr	
Processing (Melt) Temp	180 to 220	°C	
Mold Temperature	60.0 to 120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

