# LNP™ THERMOCOMP™ MX88028 compound

#### Polypropylene

**SABIC Innovative Plastics** 

#### Message:

LNP THERMOCOMP MX88028 is a compound based on Polypropylene resin containing Proprietary Filler(s).

Also known as: LNP\* THERMOCOMP\* Compound PDX-M-88028

Product reorder name: MX88028

General Information			
Filler / Reinforcement	Proprietary		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.970	g/cm³	ASTM D792
Molding Shrinkage - Flow (24 hr)	0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>1</sup>	3620	MPa	ASTM D638
Tensile Strength (Break)	48.3	МРа	ASTM D638
Tensile Elongation (Break)	3.2	%	ASTM D638
Flexural Modulus	2830	МРа	ASTM D790
Flexural Strength	75.8	МРа	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	27	J/m	ASTM D256
Unnotched Izod Impact (23°C)	390	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	136	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Rear Temperature	193 to 204	°C	
Middle Temperature	216 to 227	°C	
Front Temperature	238 to 249	°C	
Processing (Melt) Temp	227 to 249	°C	
Mold Temperature	32.2 to 48.9	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

