

Sumiliteresin® PR-51618 BI

Phenolic
SBHPP

Message:

SUMILITERESIN® PR-51618 BI is a straight novolak phenolic resin. It is generally apply for foundry.

Characteristics

SUMILITERESIN® PR-51618 BI is Flake phenolic resin with good properties in foundry manufacture. It is designed in High molecule number in order to get good anti-peel back of RCS. It is preferable add hexamine about 15%/resin when applied in resin coated sand (RCS).

General Information		
Appearance	White	
	Yellow	
Forms	flake	
Physical	Nominal Value	Unit
Flow Length (125°C)	5.00 - 7.00	cm
Thermal	Nominal Value	Unit
Melting Temperature	64.0 - 78.0	°C
Uncured Properties	Nominal Value	Unit
Gel Time (150°C)	0.83 - 1.3	min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT