

LNP™ LUBRICOMP™ IFL36 compound

Polyamide 612
SABIC Innovative Plastics

Message:

LNP LUBRICOMP* IFL36 is a compound based on Nylon 6/12 resin containing 30% Glass Fiber, 15% PTFE. Added features of this material include: Wear Resistant.

Also known as: LNP* LUBRICOMP* Compound IFL-4036

Product reorder name: IFL36

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	PTFE Lubricant (15%)		
Features	Good Wear Resistance		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.45	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.20	%	ASTM D955
Across Flow : 24 hr	0.80	%	ASTM D955
Across Flow : 24 hr	0.84	%	ISO 294-4
Flow : 24 hr	0.24	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.10	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.17	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	9970	MPa	ASTM D638
--	10300	MPa	ISO 527-2/1
Tensile Strength			
Break	154	MPa	ASTM D638
Break	157	MPa	ISO 527-2
Tensile Elongation			
Break	3.2	%	ASTM D638
Break	3.0	%	ISO 527-2
Flexural Modulus			
--	8620	MPa	ASTM D790
--	7920	MPa	ISO 178
Flexural Strength			
--	241	MPa	ASTM D790

--	232	MPa	ISO 178
Coefficient of Friction			ASTM D3702 Modified
vs. Itself - Dynamic	0.55		
vs. Itself - Static	0.51		
Wear Factor - Washer	9.00	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	140	J/m	ASTM D256
23°C ²	12	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1200	J/m	ASTM D4812
23°C ³	73	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	17.7	J	ASTM D3763
--	4.27	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	201	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁴	198	°C	ISO 75-2/Af
CLTE			
Flow : -40 to 40°C	2.5E-5	cm/cm/°C	ASTM E831
Flow : -40 to 40°C	2.6E-5	cm/cm/°C	ISO 11359-2
Transverse : -40 to 40°C	7.6E-5	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	7.7E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.12 to 0.20	%	
Rear Temperature	254 to 266	°C	
Middle Temperature	260 to 271	°C	
Front Temperature	271 to 282	°C	
Processing (Melt) Temp	271 to 277	°C	
Mold Temperature	65.6 to 93.3	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

