

TPX® DX350

Polymethylpentene Copolymer
Mitsui Chemicals America, Inc.

Message:

TPX® DX350 is a Polymethylpentene Copolymer (PMP Copolymer) material. It is available in North America for extrusion coating or fiber (spinning) extrusion.

General Information			
Appearance	Clear/Transparent		
Forms	Granules		
Processing Method	Extrusion Coating		
	Fiber (Spinning) Extrusion		

Physical	Nominal Value	Unit	Test Method
Density	0.833	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	110	g/10 min	ASTM D1238
Water Absorption (24 hr)	< 0.010	%	ASTM D570

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	87		ASTM D785

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	1800	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield, 23°C	29.0	MPa	
Break, 23°C	25.0	MPa	
Tensile Elongation (Break, 23°C)	14	%	ASTM D638
Flexural Modulus (23°C)	1500	MPa	ASTM D790
Flexural Strength (23°C)	41.0	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	19	J/m	ASTM D256
Unnotched Izod Impact Strength (23°C)	9.0	kJ/m ²	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	124	°C	ASTM D648
Vicat Softening Temperature	169	°C	ASTM D1525
Melting Temperature	233	°C	DSC
CLTE - Flow	1.2E-4	cm/cm/°C	ASTM D696

Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Strength	66	kV/mm	ASTM D149
Dielectric Constant	2.10		ASTM D150

Optical	Nominal Value	Unit	Test Method
---------	---------------	------	-------------

Refractive Index	1.460		ASTM D542
Transmittance	93.0	%	ASTM D1003
Haze	2.1	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

