

Starpylen MF007AS

Polypropylene
Eurostar Engineering Plastics

Message:
Starpylen MF007AS is a Glass Fiber Reinforced Polypropylene Injection Molding Resin

General Information			
Filler / Reinforcement	Glass Fiber		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Molding Shrinkage - Flow ¹	0.10 to 0.20	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	53.0	MPa	ISO 527-2/50
Tensile Strain (Break)	1.5	%	ISO 527-2/50
Flexural Modulus ²	4200	MPa	ISO 178
Flexural Stress	70.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ³ (23°C)	5.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ⁴ (23°C)	11	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁵			
0.45 MPa, Unannealed, 100 mm Span	145	°C	ISO 75-2/Be
1.8 MPa, Unannealed, 100 mm Span	112	°C	ISO 75-2/Ae
Injection	Nominal Value	Unit	
Drying Temperature	70.0	°C	
Drying Time	3.0	hr	
Rear Temperature	195 to 205	°C	
Middle Temperature	215 to 225	°C	
Front Temperature	225 to 250	°C	
Processing (Melt) Temp	225 to 250	°C	
Mold Temperature	30.0 to 50.0	°C	
NOTE			
1.	Tensile Bar		
2.	2.0 mm/min		
3.	80*10*4		
4.	80*10*4		
5.	120*10*4		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

