

TAROMID B 280 G8

Polyamide 6

Taro Plast S.p.A.

Message:

Polyamide 6 glass fibre reinforced 40%, high mechanical properties and good dimensional stability.
Available: all colours, UV stabilised (L), heat stabilised (H), release agent (W).

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Additive	Heat Stabilizer		
	Mold Release		
	UV Stabilizer		
Features	Good Dimensional Stability		
	Good Mold Release		
	Good UV Resistance		
	Heat Stabilized		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.47 to 1.49	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	6.0	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			ASTM D955
Flow	0.15 to 0.25	%	
Across Flow	0.40 to 0.50	%	
Water Absorption			
23°C, 24 hr	0.70 to 0.80	%	ASTM D570, ISO 62
Saturation	5.0	%	ASTM D570
Saturation, 23°C	5.0	%	ISO 62
Granule Humidity	< 0.15	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	124		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	12500	MPa	ASTM D638, ISO 527-2
Tensile Strength (Break)	208	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	2.2	%	ASTM D638, ISO 527-2
Flexural Modulus	11500	MPa	ASTM D790, ISO 178
Flexural Stress			

--	310	MPa	ISO 178
Break	310	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ¹ (23°C)	15	kJ/m ²	ASTM D256, ISO 179
Charpy Unnotched Impact Strength ²			ISO 179, ASTM D256
-20°C	46	kJ/m ²	
23°C	58	kJ/m ²	
Notched Izod Impact (23°C, 3.20 mm)	150	J/m	ISO 180, ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	214	°C	ASTM D648, ISO 75-2/A
Continuous Use Temperature			
-- ³	100	°C	IEC 60216
-- ⁴	130	°C	IEC 60216
-- ⁵	140	°C	IEC 60216
-- ⁶	180	°C	IEC 60167
Vicat Softening Temperature	216	°C	ISO 306/B50, ASTM D1525 ⁷
Ball Pressure Test (165°C)	Pass		VDE 0470
Melting Temperature	222	°C	ASTM D211, ISO 121
CLTE - Flow (-30 to 30°C)	2.5E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	7.0E+15	ohms·cm	ASTM D257
Dielectric Strength (2.00 mm)	26	kV/mm	ASTM D149
Comparative Tracking Index (Solution A)	550	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.970 mm)	HB		UL 94
Glow Wire Ignition Temperature (2.00 mm)	750	°C	IEC 60695-2-13
Oxygen Index	24	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature			
--	80.0 to 90.0	°C	
Pre-heater	80.0 to 100	°C	
Drying Time			
--	1.0	hr	
Pre-heater	3.0	hr	
Processing (Melt) Temp	230 to 260	°C	
Mold Temperature	90.0 to 120	°C	
Injection Rate	Moderate-Fast		
NOTE			
1.	6x4x50 mm		
2.	6x4x50 mm		
3.	20000 hrs		

4.	Heat Stabilized, 20000 hrs
5.	Short Term
6.	Heat Stabilized, Short Term
7.	Rate A (50°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

