

ENFLEX VL-120-90A

Polypropylene + EPDM Rubber

Ravago Group

Message:

Standard, fully vulcanized EPDM/PP series

General Information			
Physical	Nominal Value	Unit	Test Method
Density	0.960	g/cm ³	ISO 2781
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	90		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% Strain	5.30	MPa	
300% Strain	7.50	MPa	
Tensile Stress (Break)	12.0	MPa	ISO 37
Tensile Elongation (Break)	480	%	ISO 37
Tear Strength	78	kN/m	ISO 34-1
Compression Set			ASTM D395B
23°C, 22 hr	26	%	
70°C, 22 hr	38	%	
100°C, 22 hr	47	%	
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-60.0	°C	ISO 974
Maximum Dynamic Service Temperature	135	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT