

Nylfor® A2 E6/2A NATURALE

Polyamide 66

SO.F.TER. SPA

Message:

Nylfor® A2 E6/2A NATURALE is a Polyamide 66 (Nylon 66) material. It is available in Europe, Latin America, or North America for injection molding. Important attributes of Nylfor® A2 E6/2A NATURALE are:
Flame Rated
REACH Compliant

General Information			
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm ³	ASTM D792
Molding Shrinkage	1.5	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	7.5	%	
Equilibrium, 23°C, 50% RH	2.4	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ASTM D638
Tensile Strength (Yield)	55.0	MPa	ASTM D638
Tensile Elongation (Break)	60	%	ASTM D638
Flexural Modulus	2000	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	21	kJ/m ²	ISO 179/1eA
Notched Izod Impact (23°C)	200	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	75.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	4.0	hr	
Rear Temperature	260	°C	
Middle Temperature	270	°C	

Front Temperature	280	°C
Mold Temperature	60.0 to 80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

