

RABALON® FJ7371C

Thermoplastic Elastomer

Mitsubishi Chemical Performance Polymers, Inc.

Message:

RABALON® FJ7371C is a Thermoplastic Elastomer (TPE) material. It is available in Asia Pacific, Europe, or North America.

General Information			
Appearance	Clear/Transparent		
Physical	Nominal Value	Unit	Test Method
Density	0.890	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	55	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	74		ISO 7619
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	3.00	MPa	ISO 37
Tensile Stress (Break)	8.00	MPa	ISO 37
Tensile Elongation (Break)	650	%	ISO 37
Tear Strength	43	kN/m	ISO 34-1
Optical	Nominal Value	Unit	Test Method
Haze (2000 μm)	23	%	ISO 14782

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

