Ateva® 2842A

Ethylene Vinyl Acetate Copolymer

Celanese EVA Performance Polymers

Message:

This resin is commonly used for hot melt coating and adhesive applications.

| General Information | | | |
|---|----------------------|----------|-------------|
| Additive | Antioxidant | | |
| Features | Antioxidant | | |
| | Copolymer | | |
| | | | |
| Uses | Adhesives | | |
| | Coating Applications | | |
| | | | |
| Agency Ratings | EC 1907/2006 (REACH) | | |
| Forms | Pellets | | |
| Processing Method | Extrusion Coating | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.941 | g/cm³ | ASTM D1505 |
| Melt Mass-Flow Rate (MFR) (125°C/0.325 | | | |
| kg) | 400 | g/10 min | ASTM D1238 |
| Vinyl Acetate Content | 28.0 | wt% | |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness | | | ASTM D2240 |
| Shore A | 67 | | |
| Shore D | 14 | | |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength ¹ (Break) | 3.00 | MPa | ASTM D638 |
| Tensile Elongation ² (Break) | 600 | % | ASTM D638 |
| Flexural Modulus - 1% Secant | 12.0 | MPa | ASTM D790 |
| Thermal | Nominal Value | Unit | Test Method |
| Peak Melting Temperature | 65.0 | °C | ASTM D3418 |
| Ring and Ball Softening Point | 84 | °C | ASTM E28 |
| Extrusion | Nominal Value | Unit | |
| Melt Temperature | < 210 | °C | |
| NOTE | | | |
| 1. | Type IV, 50 mm/min | | |
| 2. | Type IV, 50 mm/min | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

