

Starglas FF001

High Density Polyethylene
Eurostar Engineering Plastics

Message:

Starglas FF001 is a Glass Fiber Reinforced High Density Polyethylene Resin

General Information			
Filler / Reinforcement	Glass Fiber		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.00	g/cm ³	ISO 1183
Molding Shrinkage - Flow (4.00 mm)	0.70	%	Internal Method
Water Absorption (Equilibrium, 23°C, 50% RH)	0.0	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1700	MPa	ISO 527-2/1
Tensile Stress (Yield)	28.0	MPa	ISO 527-2/5
Tensile Strain (Yield)	3.6	%	ISO 527-2/5
Flexural Modulus ¹	1500	MPa	ISO 178
Flexural Stress	36.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ² (23°C)	5.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	25	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴ (1.8 MPa, Unannealed, 64.0 mm Span)	62.0	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0	hr	
Rear Temperature	195 to 205	°C	
Middle Temperature	210 to 220	°C	
Front Temperature	220 to 230	°C	
Processing (Melt) Temp	230	°C	
Mold Temperature	40.0 to 55.0	°C	
NOTE			
1.	2.0 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

