

Anjacom® 250-H/GF15

Polyamide 6
Almaak International GmbH

Message:

Anjacom® 250-H/GF15 is a Polyamide 6 (Nylon 6) material filled with 15% glass fiber. It is available in Europe for injection molding.
Important attributes of Anjacom® 250-H/GF15 are:
Flame Rated
Heat Stabilizer

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.23	g/cm³	ISO 1183
Water Absorption			ISO 62
23°C, 24 hr	8.5	%	
Equilibrium, 23°C, 50% RH	2.6	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6000	MPa	ISO 527-2/1
Tensile Stress (Break)	125	MPa	ISO 527-2/5
Tensile Strain (Break)	3.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	45	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	190	°C	ISO 75-2/A
Vicat Softening Temperature	200	°C	ISO 306/B50
Ball Indentation Temperature	210	°C	IEC 60598-1
Melting Temperature (DSC)	220	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Electric Strength	25	kV/mm	IEC 60243-1
Comparative Tracking Index	550	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Glow Wire Flammability Index (3.00 mm)	650	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0 to 10	hr	

Suggested Max Moisture	0.10	%
Processing (Melt) Temp	240 to 260	°C
Mold Temperature	80.0 to 100	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

