

Plavis® ESD

Thermoplastic Polyimide

Comco Nylon GmbH

Message:

PLAVIS is a super engineering plastic. PLAVIS polyimide has a unique chemical structure with some of the highest properties available. Nitrogen bonded to 3 carbons is the critical part of the chain and imparts the plastic with remarkable features and benefits.

DAELIM makes PLAVIS isostatic molded rods have uniform properties in all directions.

General Information			
Features	The degassing effect is low to no Heat resistance, high Flame retardancy		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.44	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale, Compression Molded)	90 - 105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D1708
Fracture, 23°C	83.3	MPa	ASTM D1708
Fracture, 260°C	39.2	MPa	ASTM D1708
Tensile Elongation ²			ASTM D1708
Fracture, 23°C	7.0	%	ASTM D1708
Fracture, 260°C	6.0	%	ASTM D1708
Flexural Modulus (23°C, Compression Molded)	3430	MPa	ASTM D790
Flexural Strength (23°C, Compression Molded)	108	MPa	ASTM D790
Compressive Modulus ³	2450	MPa	ASTM D695
Compressive Strength ⁴			ASTM D695
1% strain, 23°C	24.5	MPa	ASTM D695
10% strain, 23°C	147	MPa	ASTM D695
Coefficient of Friction ⁵	0.32		
Wear Rate	33	mm/sec	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Compression Molded)	49	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Thermal Conductivity ⁶ (25°C)	0.37	W/m/K	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity ⁷	1.0E+6 - 1.0E+9	ohms	ASTM D257

NOTE	
1.	Compression Molded
2.	Compression Molded
3.	Compression Molded
4.	Compression Molded
5.	Compression Molded
6.	Compression Molded
7.	Compression Molded

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

