

KOPLA PA66 KUG1330BK

Polyamide 66

KOPLA Co., Ltd.

Message:

KOPLA PA66 KUG1330BK is a Polyamide 66 (Nylon 66) material filled with glass fiber. It is available in Asia Pacific. Primary attribute of KOPLA PA66 KUG1330BK: Flame Rated.
Typical applications include:
Automotive
Electrical/Electronic Applications
Engineering/Industrial Parts
Tanks

General Information			
Filler / Reinforcement	Glass Fiber		
Uses	Automotive Exterior Parts		
	Automotive Under the Hood		
	Electrical Parts		
	Electrical/Electronic Applications		
	Tanks		
	Thin-walled Parts		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30 to 0.80	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.70	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	122		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	186	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	3.5	%	ASTM D638
Flexural Modulus (23°C)	9320	MPa	ASTM D790
Flexural Strength (23°C)	265	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	140	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	255	°C	
1.8 MPa, Unannealed	250	°C	
Melting Temperature	260	°C	
CLTE - Flow	3.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257

Dielectric Strength	25	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

