# ColorRx® PP1-0800RX

### Polypropylene Homopolymer

LTL Color Compounders, Inc.

#### Message:

A biocompatible, Polypropylene homopolymer for healthcare applications.

| General Information              |                          |          |             |
|----------------------------------|--------------------------|----------|-------------|
| Features                         | Homopolymer              |          |             |
|                                  | Biocompatibility         |          |             |
| Uses                             | Medical/nursing supplies |          |             |
| Agency Ratings                   | ISO 10993                |          |             |
|                                  | USP Class VI             |          |             |
|                                  |                          |          |             |
| Physical                         | Nominal Value            | Unit     | Test Method |
| Specific Gravity                 | 0.900                    | g/cm³    | ASTM D792   |
| Melt Mass-Flow Rate (MFR) (190°C | 2/2.16                   |          |             |
| kg)                              | 7.5                      | g/10 min | ASTM D1238  |
| Mechanical                       | Nominal Value            | Unit     | Test Method |
| Tensile Strength (Yield)         | 30.3                     | MPa      | ASTM D638   |
| Tensile Elongation               |                          |          | ASTM D638   |
| Yield                            | 10                       | %        | ASTM D638   |
| Fracture                         | > 50                     | %        | ASTM D638   |
| Thermal                          | Nominal Value            | Unit     | Test Method |
| Deflection Temperature Under Loa | id (0.45                 |          |             |
| MPa, Unannealed)                 | 82.8                     | °C       | ASTM D648   |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

