# Zhongfa PP GR-10H

## Polypropylene

### Yuyao Zhongfa Engineering Plastics Co. Ltd.

#### Message:

Zhongfa PP GR-10H is a polypropylene material, and the filler is 10% glass fiber reinforced material. This product is available in the Asia-Pacific region and is processed by injection molding. The main features of Zhongfa PP GR-10H are: chemical resistance Heat resistance Typical application areas include: electrical appliances industrial applications Automotive Industry

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Features	Good liquidity		
	Good chemical resistance		
	Heat resistance, medium		
Uses	Electrical appliances		
	Industrial application		
	Application in Automobile Field		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.00	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.60 - 0.90	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	55.0	MPa	ASTM D638
Flexural Modulus	2800	MPa	ASTM D790
Flexural Strength	70.0	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	140	°C	ASTM D648
Additional Information			
Notched Izod Impact, ASTM D256: 9 kJ/m <sup>2</sup> U	nnotched Izod Impact, ASTM D256: 18	kJ/m²	
Injection	Nominal Value	Unit	
Drying Temperature	90.0 - 95.0	°C	
Drying Time	2.0 - 3.0	hr	
Processing (Melt) Temp	215 - 245	°C	
Mold Temperature	45.0 - 80.0	°C	

Injection	Pressure
-----------	----------

MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

