# Geon<sup>™</sup> Vinyl Flexible R242BE

### Flexible Polyvinyl Chloride

#### PolyOne Corporation

#### Message:

Geon<sup>™</sup> Vinyl Flexible R242BE is a Flexible Polyvinyl Chloride product. It can be processed by coextrusion, extrusion, injection molding, or profile extrusion and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of Geon<sup>™</sup> Vinyl Flexible R242BE include hose/tubing, construction applications and furniture. Characteristics include: Low Gloss

UV Stabilized

General Information			
Additive	Biocide		
	UV Stabilizer		
Features	Low Gloss		
	UV Absorbing		
Uses	Construction Applications		
	Furniture		
	Hose		
	Profiles		
	Tubing		
Forms	Pellets		
Processing Method	Coextrusion		
	Extrusion		
	Injection Molding		
	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	70		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Break)	13.8	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	350	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-23.9	°C	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index (3.18 mm)	23	%	ASTM D2863
Injection	Nominal Value	Unit	

Processing (Melt) Temp	185 to 196	°C
Extrusion	Nominal Value	Unit
Melt Temperature	171 to 179	°C
NOTE		
1.	Type IV, 510 mm/min	
2.	Type IV, 510 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

