Daelim Po1y® 5070(UV)

High Density Polyethylene

DAELIM INDUSTRIAL CO., LTD.

Message:

Daelim Po1y® 5070(UV) is a high density polyethylene product. It can be processed by blow molding and is available in the Asia-Pacific region. Daelim Po1y® 5070(UV) applications include container and food contact applications. Features include: High resistance to environmental stress fracture (ESCR) Good processability accessible food Good UV resistance Impact resistance

| General Information | | | |
|---|--|----------|-------------|
| Features | Ultra-high impact resistance | | |
| | High ESCR (Stress Cracking Resistance) | | |
| | High melt stability | | |
| | Good UV resistance | | |
| | Workability, good | | |
| | Compliance of Food Exposure | | |
| Uses | Industrial container | | |
| Agency Ratings | ASTM D 1248, III, Class A, Cat. 5 | | |
| | FDA 21 CFR 177.1520 | | |
| | | | |
| Forms | Particle | | |
| Processing Method | Blow molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.952 | g/cm³ | ASTM D1505 |
| Melt Mass-Flow Rate (MFR) (190°C/21.6 | | | |
| kg) | 6.5 | g/10 min | ASTM D1238 |
| Environmental Stress-Cracking Resistance (F50) | > 800 | hr | ASTM D1693B |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield) | 26.5 | МРа | ASTM D638 |
| Tensile Elongation (Break) | 600 | % | ASTM D638 |
| Flexural Modulus | 1080 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (-20°C) | No Break | | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Brittleness Temperature | -76.0 | °C | ASTM D746 |
| Additional Information | | | |

| Injection | Nominal Value | Unit |
|------------------------|---------------|------|
| Processing (Melt) Temp | 190 - 230 | °C |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

