

PREPERM® L300

Polyphenylene Ether

Premix Oy

Message:

PREPERM® L300 is a special compound with elevated dielectric constants of 3.0.

PREPERM® L300 is based on Premix proprietary PPE technology. Extremely low dissipation factor (0.0005) makes PREPERM® L300 an excellent material for high frequency applications. PREPERM® L300 offers stable dielectric constant over wide frequency and wide temperature range. PREPERM® retains its physical properties at very low (-78°C) temperatures. PREPERM® L300 can be injection moulded or extruded.

Applications include structural parts for antennas in base stations, point to point, wlan, mobile phones etc. Devices made out of PREPERM® L300 can operate at very high frequencies as PREPERM® L300 offers stable performance even at 120 GHz.

General Information	
Features	Low temperature strength
	Low Temperature Flexibility
Uses	Electrical/Electronic Applications
	Electrical components
RoHS Compliance	RoHS compliance
Forms	Particles
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/5.0 kg)	16	g/10 min	ISO 1133
Molding Shrinkage - Flow	1.0	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield	55.0	MPa	ISO 527-2
4.00 mm	47.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	10	%	ISO 527-2
Fracture, 4.00mm	30	%	ISO 527-2
Flexural Modulus (4.00 mm)	2000	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact ¹			ISO 180
-78°C	16	kJ/m ²	ISO 180
-20°C	20	kJ/m ²	ISO 180
23°C	No Break		ISO 180
Unnotched Izod Impact Strength ²			ISO 180
-78°C	No Break		ISO 180

-20°C	No Break		ISO 180
23°C	No Break		ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	176	°C	ISO 75-2/Bf
1.8 MPa, not annealed	155	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	193	°C	ISO 306/A50
--	161	°C	ISO 306/B50
Electrical	Nominal Value		Test Method
Dielectric Constant (1.00 GHz)	3.00		Internal method
Dissipation Factor (1.00 GHz)	5.0E-4		Internal method
Flammability	Nominal Value		Test Method
Flame Rating (4.00 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120 - 140	°C	
Drying Time	2.0 - 4.0	hr	
Processing (Melt) Temp	290 - 310	°C	
Mold Temperature	80.0 - 140	°C	
Injection Pressure	60.0 - 80.0	MPa	
Injection Rate	Moderate		
Extrusion	Nominal Value	Unit	
Drying Temperature	120 - 140	°C	
Drying Time	2.0 - 4.0	hr	
Melt Temperature	260 - 280	°C	
Die Temperature	260 - 300	°C	
Extrusion instructions			
Tool / roll temperature : 60 - 180°C			
NOTE			
1.	4 mm thickness		
2.	4 mm thickness		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT