

Nypol® PA A3 G10 UV PRTA011 NR436

Polyamide 66

Petropol Industry and Trade of Polymers LTDA

Message:

Polyamide 6.6 in black color reinforced with 10% of fiberglass, UV resistance, good set of thermal and mechanical properties. Ideal for injection molding.

General Information				
Additive	UV Stabilizer			
Features	Good UV Resistance			
Appearance	Black			
Processing Method	Injection Molding			
Resin ID (ISO 1043)	>PA 6.6 GF10<			
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.21	--	g/cm ³	ASTM D792
Water Absorption				ASTM D570
Saturation	7.1	--	%	
Equilibrium	2.2	--	%	
Ash Content	8.0 to 12	--	%	ASTM D2584
Deformation Under Load - 27.6 MPa (50°C)	1.1	--	%	ASTM D621
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	5500	3500	MPa	ASTM D638
Tensile Strength				ASTM D638
Break	118	75.0	MPa	
--	120	80.0	MPa	
Tensile Elongation (Break)	3.0 to 3.2	8.0 to 12	%	ASTM D638
Flexural Modulus	5300	3000	MPa	ASTM D790
Flexural Strength	190	140	MPa	ASTM D790
Shear Strength	75.0	--	MPa	ASTM D732
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-40°C	4.0	4.0	kJ/m ²	
23°C	4.5	6.0	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179
-30°C	30	30	kJ/m ²	
23°C	32	70	kJ/m ²	
Notched Izod Impact	48	52	J/m	ASTM D256
Notched Izod Impact (Area)				ASTM D256

-40°C	4.00	3.00	kJ/m ²	
23°C	4.50	4.00	kJ/m ²	
Unnotched Izod Impact (Area)				ASTM D256
-30°C	35.0	28.0	kJ/m ²	
23°C	40.0	55.0	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	230	--	°C	ASTM D648
Melting Temperature	250 to 265	--	°C	ASTM D2117
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+16	--	ohms·cm	IEC 60093
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating	HB	--		UL 94
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0		hr	
Suggested Max Moisture	0.20		%	
Processing (Melt) Temp	260 to 280		°C	
Mold Temperature	65.0 to 120		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

