# 3M<sup>™</sup> Dyneon<sup>™</sup> PTFE Compound TF 8637

#### Polytetrafluoroethylene

#### 3M Advanced Materials Division

#### Message:

3M<sup>™</sup> Dyneon<sup>™</sup> PTFE Compound TF 8637 is a free-flowing suspension PTFE compound containing 26.5% filler consisting of carbon, glass fibre, molybdenum-disulfide and maroon pigment for compression and automatic moulding.

Special Features

Increased thermal dimensional stability

Increased surface hardness

Improved deformation under load

Reduced friction & wear

Good chemical stability

High limiting oxygen index (LOI)

Low friction behaviour

Very good mechanical properties

Exceptional temperature resistance

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
	Carbon fiber reinforced material		
Additive	Pigment		
	Molybdenum disulfide lubricant		
Features	Low friction coefficient		
rediates	Lubrication		
	Edblication		
Uses	Seals		
	Application in Automobile Field		
Appearance	Maroon		
Forms	Powder		
Processing Method	Compression molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.15	g/cm³	ASTM D4745-06
Apparent Density	0.70	g/cm³	ASTM D4894-07
Molding Shrinkage - Flow	2.5	%	ASTM D4894-07
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	71		DIN 53505
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	13.5	МРа	ASTM D4745-06
Tensile Elongation (Break)	130	%	ASTM D4745-06

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2