

POLYelast TPE EC90 D50 P05B

Polypropylene + EPDM Rubber

Polykemi AB

Message:

PP/EPDM

General Information			
Physical	Nominal Value	Unit	Test Method
Density	0.930	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.2 to 1.5	%	
Flow	1.2 to 1.5	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	55		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	15.0	MPa	ISO 527-2
Tensile Strain (Break)	300	%	ISO 527-2
Flexural Modulus (23°C)	650	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	15	kJ/m ²	
23°C	30	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ¹ (0.45 MPa, Unannealed)	87.0	°C	ISO 75-2/B
NOTE			
1.	120°C/hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT