

LAMINEX® 2101

Phenol Formaldehyde Resin

Schwartz Technical Plastic

Message:

Cotton fabric clips, phenolic resin impregnated, compression moulded

Applications:

Bearing segments

Prismatic bearings

General Information			
Uses	Fabric		
	Bearing		
Processing Method		Compression molding	
Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	ISO 1183
Water Absorption (Saturation, 23°C)	2.2	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	130	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield	40.0 - 60.0	MPa	ISO 527-2
Fracture	60.0	MPa	ISO 527-2
Flexural Modulus	7000 - 10000	MPa	ISO 178
Compressive Stress	140	MPa	ISO 604
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	> 8.0	kJ/m ²	ISO 180
Unnotched Izod Impact Strength	> 8.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	3.0E-5 - 4.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.30	W/m/K	ISO 8302
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+9	ohms	IEC 60093
Dielectric Strength	20	kV/mm	IEC 60243-1
Dielectric Constant (1 kHz)	6.00 - 10.0		IEC 60250
Dissipation Factor (1 kHz)	0.40		IEC 60250
Additional Information			

Safe Temperature Range, short periods: 150°C Safe Temperature Range, permanent: 125°C Moisture Absorption under normal air condition: 300 mg Penetration Resistance: 1e9 ohm-cm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT